

Coating slides with poly L-lysine:

0.5 ml of poly-l-lysine solution (0.1 mg/ml in distilled water) was dropped on to each coverslip to cover the glass surface and left on for about 3 h. The coverslip was then rinsed three times with sterile water. Cultures were incubated in MEM for one day